

# Castone<sup>®</sup> Dental Stone

**DENTSPLY**  
TRUBYTE

## TYPE III WHITE

**25 Lbs.** (11.4 kg.)  
ReOrder #99047



\*+D001990470+\*

**50 Lbs.** (22.7 kg.)  
ReOrder #99046



\*+D001990460/\*

**100 Lbs.** (45.4 kg.)  
ReOrder #99049



\*+D0019904900\*

## CREAM

**25 Lbs.** (11.4 kg.)  
ReOrder #99043



\*+D001990430.\*

**50 Lbs.** (22.7 kg.)  
ReOrder #99044



\*+D001990440\_\*

**100 Lbs.** (45.4 kg.)  
ReOrder #99045



\*+D001990450\$\*

For Dental Use Only

**Caution:** Inhalation of powder may be hazardous to your health.

CASTONE is a high quality, high strength dental stone used for dental casts, investing and articulator mounting.

### Directions:

**For Manual Mixing-** Add 100g powder to 30 cc water in a clean, dry mixing bowl. Soak for 30 seconds, then vigorously spatulate for 30 seconds.

**For Mechanical Mixing-** Add 100g powder to 30 cc water in a clean, dry mixing bowl. Soak until powder is wet. Mix for 20 seconds, 200 to 300 turns of the blade.

Distributed By:  
DENTSPLY Trubyte  
DENTSPLY International Inc.  
York, PA 17405-0872

1-800-786-0085      www.dentsply.com

Lot No.

### Properties:

Powder/Water Ratio	100 g: 30 cc
Compression Strength	Wet 3,000 psi Dry 8,000 psi
Setting Time	8-10 minutes
Setting Expansion	0.08%

**Storage:** Gypsum materials are subject to deterioration when exposed to the atmosphere. Store this product at 59°F to 86°F. Keep container tightly closed once seal is broken to protect contents from moisture and high humidity.

NOT RETURNABLE FOR CREDIT IF SEAL IS BROKEN.

Made & Printed in U.S.A.      4235-E Rev. A (2/99)

Exp. Date